

SECTION I - GENERAL INFORMATION

Trade Name & Synonyms
 NON-SHOOT PART A
 FORMULA MIXTURE --> X
 Manufacturer's Name:
 UNIFIED LABOR, DIV. OF NCR CORP.
 Address:
 BOX 132170
 IRVING, TEXAS 75015
 Prepared By:
 J. B. Johnson/ChemLab
 Product Code Number
 4714A
 Emergency Phone Number
 800-424-9300

SECTION II - HAZARDOUS INGREDIENTS

THE HAZARDS PRESENTED BELOW ARE THOSE OF THE INDIVIDUAL COMPONENTS

SECTION III - PHYSICAL DATA									
Material Name (Typical)	N/A		Specific Gravity (60-60)	2.49					
Surfactant	N/A		Color:	GRAY					
Surfactant Concentration (g/L)	N/A		Odor:	COOKIES					
Surfactant Type	N/A		Odor:	COOKIES					
Surfactant Grade	N/A		Clarity:	GRAY					
Surfactant Volatile by Volume	N/A		Evaporation Rate (ml A/cm ² /hr)	N/A					
Surfactant Solubility	N/A		Viscosity	POWDER					

SECTION IV - FIRE AND EXPLOSION HAZARD

[illegible]

SECTION V - HEALTH HAZARD DATA

Worksheet Label Value: _____
Worksheet Title: _____
Worksheet Section ID: _____
Worksheet Section Name: _____
Worksheet Section Description: _____
Worksheet Section Author: _____
Worksheet Section Date: _____
Worksheet Section Version: _____
Worksheet Section Status: _____
Worksheet Section Comments: _____
Worksheet Section History: _____
Worksheet Section Details: _____
Worksheet Section Notes: _____
Worksheet Section Footer: _____

SECTION V - HEALTH HAZARD DATA (Continued)

Emergency and First Aid Procedures:

-Inhalation:
IF DUST IS INHALED, REMOVE FROM THE AREA TO FRESH AIR. HAVE THE PERSON BLOW THEIR NOSE TO REMOVE THE SUBSTANCE FROM THE NOSE. -WASHES AND KEEP FROM INHAALING FURTHER. SEEK MEDICAL ATTENTION IF DISCOMFORT OCCURS.

-Eye Contact:
WASH THE EYES WITH WATER. REMOVE ANY CONTACT LENSES AND CONTINUE FLUSHING WITH PLENTY OF WATER FOR SEVERAL MINUTES. SEEK MEDICAL ATTENTION IF IRRITATION DEVELOPS.

-Skin Contact:
WASH AWAY MATERIALS WITH A CLOTH WHILE REMOVING CONTAMINATED CLOTHING AND SHOES. WASH THOROUGHLY WITH SOAP AND WATER. SEEK MEDICAL ATTENTION IF IRRITATION DEVELOPS. DISPOSE OF CLEAN CLOTHING AND SHOES.

-Ingestion:
GIVE 3 TO 4 GLASSES OF WATER, BUT DO NOT INDUCE VOMITING. IF VOMITING OCCURS, GIVE FLUIDS AGAIN. SEEK MEDICAL ATTENTION IF DISCOMFORT OCCURS.

-Notes to Physicians:
THERE IS NO SPECIFIC ANTIDOTE. TREAT THE PATIENT SYMPTOMATICALLY.

SECTION VI - TOXICITY INFORMATION

[illegible]

SECTION VII - REACTIVITY DATA

[illegible]

SECTION VIII - SPILL OR LEAK PROCEDURES

How to be taken if material is released or spilled:
 1. Contain the contaminated area and avoid creating dusty conditions. Wear appropriate protective clothing. Transfer bulk into a properly labeled container for incineration or disposal. If necessary wash area with water. Remove product from contaminated soil or from entering stream and discharge treated and incinerate or dispose of water.

State Disposal Method(s):
 Incineration in accordance with all Federal, State, and local regulations.

Submitting Agent:
 I/A

SECTION IX - SPECIAL PROTECTION INFORMATION

[illegible]

PROPERTY CLASSIFIED BY METHOD
STANDARD FOR EYE AND FACE
PROTECTION, 29 CFR 1910.133.
NATION PREVENTS THE LIKELIHOOD OF EYE CONTACT, KNUTIVE CONTACT WITH ORIGIN'S PROVISIONAL PROTECTIVE EQUIPMENT (PPE)

Other protection:
WILAR CONCRETE-DUTY WORK CLOTHES AND SHOES

Storage Temperature:	Indoor--> X	Outdoor-->	Heated-->	Refrigerated-->
Material Name: Concrete				
Material Number: 1				
Material Description: Concrete				
Material Quantity: 1000				
Material Unit: cubic yard				
Material Location: 1000				
Material Status: 1000				
Material Type: 1000				
Material Color: 1000				
Material Finish: 1000				
Material Texture: 1000				
Material Weight: 1000				
Material Volume: 1000				
Material Area: 1000				
Material Perimeter: 1000				
Material Height: 1000				
Material Depth: 1000				
Material Width: 1000				
Material Length: 1000				
Material Thickness: 1000				
Material Diameter: 1000				
Material Radius: 1000				
Material Circumference: 1000				
Material Surface Area: 1000				
Material Volume: 1000				
Material Weight: 1000				
Material Density: 1000				
Material Specific Gravity: 1000				
Material Porosity: 1000				
Material Absorption: 1000				
Material Permeability: 1000				
Material Coefficient of Expansion: 1000				
Material Modulus of Elasticity: 1000				
Material Poisson's Ratio: 1000				
Material Compressive Strength: 1000				
Material Tensile Strength: 1000				
Material Flexural Strength: 1000				
Material Shear Strength: 1000				
Material Bond Strength: 1000				
Material Adhesion: 1000				
Material Cohesion: 1000				
Material Friction: 1000				
Material Stiffness: 1000				
Material Ductility: 1000				
Material Toughness: 1000				
Material Impact Resistance: 1000				
Material Fatigue Resistance: 1000				
Material Creep Resistance: 1000				
Material Shrinkage: 1000				
Material Swelling: 1000				
Material Expansion: 1000				
Material Contraction: 1000				
Material Settlement: 1000				
Material Uplift: 1000				
Material Sliding: 1000				
Material Rotation: 1000				
Material Torsion: 1000				
Material Bending: 1000				
Material Twisting: 1000				
Material Stretching: 1000				
Material Compression: 1000				
Material Tension: 1000				
Material Shear: 1000				
Material Bond: 1000				
Material Adhesion: 1000				
Material Cohesion: 1000				
Material Friction: 1000				
Material Stiffness: 1000				
Material Ductility: 1000				
Material Toughness: 1000				
Material Impact Resistance: 1000				
Material Fatigue Resistance: 1000				
Material Creep Resistance: 1000				
Material Shrinkage: 1000				
Material Swelling: 1000				
Material Expansion: 1000				
Material Contraction: 1000				
Material Settlement: 1000				
Material Uplift: 1000				
Material Sliding: 1000				
Material Rotation: 1000				
Material Torsion: 1000				
Material Bending: 1000				
Material Twisting: 1000				
Material Stretching: 1000				
Material Compression: 1000				
Material Tension: 1000				
Material Shear: 1000				
Material Bond: 1000				
Material Adhesion: 1000				
Material Cohesion: 1000				
Material Friction: 1000				
Material Stiffness: 1000				
Material Ductility: 1000				
Material Toughness: 1000				
Material Impact Resistance: 1000				

Storage Temperature:	Indoor--> X	Outdoor-->	Heated-->	Refrigerated-->
Material Name: Concrete				
Material Number: 1				
Material Description: Concrete				
Material Quantity: 1000				
Material Unit: cubic yard				
Material Location: 1000				
Material Status: 1000				
Material Type: 1000				
Material Color: 1000				
Material Finish: 1000				
Material Texture: 1000				
Material Weight: 1000				
Material Volume: 1000				
Material Area: 1000				
Material Perimeter: 1000				
Material Height: 1000				
Material Depth: 1000				
Material Width: 1000				
Material Length: 1000				
Material Thickness: 1000				
Material Diameter: 1000				
Material Radius: 1000				
Material Circumference: 1000				
Material Surface Area: 1000				
Material Volume: 1000				
Material Weight: 1000				
Material Density: 1000				
Material Specific Gravity: 1000				
Material Porosity: 1000				
Material Absorption: 1000				
Material Permeability: 1000				
Material Coefficient of Expansion: 1000				
Material Modulus of Elasticity: 1000				
Material Poisson's Ratio: 1000				
Material Compressive Strength: 1000				
Material Tensile Strength: 1000				
Material Flexural Strength: 1000				
Material Shear Strength: 1000				
Material Bond Strength: 1000				
Material Adhesion: 1000				
Material Cohesion: 1000				
Material Friction: 1000				
Material Stiffness: 1000				
Material Ductility: 1000				
Material Toughness: 1000				
Material Impact Resistance: 1000				
Material Fatigue Resistance: 1000				
Material Creep Resistance: 1000				
Material Shrinkage: 1000				
Material Swelling: 1000				
Material Expansion: 1000				
Material Contraction: 1000				
Material Settlement: 1000				
Material Uplift: 1000				
Material Sliding: 1000				
Material Rotation: 1000				
Material Torsion: 1000				
Material Bending: 1000				
Material Twisting: 1000				
Material Stretching: 1000				
Material Compression: 1000				
Material Tension: 1000				
Material Shear: 1000				
Material Bond: 1000				
Material Adhesion: 1000				
Material Cohesion: 1000				
Material Friction: 1000				
Material Stiffness: 1000				
Material Ductility: 1000				
Material Toughness: 1000				
Material Impact Resistance: 1000				
Material Fatigue Resistance: 1000				
Material Creep Resistance: 1000				
Material Shrinkage: 1000				
Material Swelling: 1000				
Material Expansion: 1000				
Material Contraction: 1000				
Material Settlement: 1000				
Material Uplift: 1000				
Material Sliding: 1000				
Material Rotation: 1000				
Material Torsion: 1000				
Material Bending: 1000				
Material Twisting: 1000				
Material Stretching: 1000				
Material Compression: 1000				
Material Tension: 1000				
Material Shear: 1000				
Material Bond: 1000				
Material Adhesion: 1000				
Material Cohesion: 1000				
Material Friction: 1000				
Material Stiffness: 1000				
Material Ductility: 1000				
Material Toughness: 1000				
Material Impact Resistance: 1000				

PRECAUTIONS TO BE TAKEN IN HANDLING AND STORING:
STAY AWAY FROM BATHING IN THE OCEAN, CONTACT WITH
WOUND COMPANIMENTS, TIGHTLY CLOSED WHEN NOT IN USE. AVOID CREATING TURBID CONDITIONS. SUN, BROKEN PLASTIC

Other Prevalence

KEPT OUT OF REACH OF CHILDREN. READ THE LABEL CAREFULLY BEFORE USING THIS PRODUCT. FOLLOW THE LABEL DIRECTIONS.

Chemical Name

Card Number

Order & Limit

Chemical Name

Card Number

Order & Limit

2. THRESHOLD LIMIT VALUES FOR CHEMICAL SUBSTANCES AND PHYSICAL AGENTS AND BIOLOGICAL AGENTS INDEXED, AACH, 2003

- [illegible]